



TECHNICAL SPECIFICATION SHEET

Range

Kansas

Design

Figured woven

Composition $\pm 3\%$ per compound

100% Polyester

Useable Fabric Width (cm)

138

Pattern Repeat (cm)

Vertical	n/a	Horizontal	n/a
----------	-----	------------	-----

Martindale (rubs)

$\geq 45,000$

Seam (mm)

Warp	$\leq 5\text{mm}$	Weft	$\leq 3\text{mm}$
------	-------------------	------	-------------------

Tensile (N)

Warp	$\geq 1000\text{N}$	Weft	$\geq 1000\text{N}$
------	---------------------	------	---------------------

Tear (N)

Warp	$\geq 200\text{N}$	Weft	≥ 140
------	--------------------	------	------------

Pilling Grade

@2000 rubs	4-5	@5000 rubs	4-5
------------	-----	------------	-----

Bursting (kPa)

n/a

Weight (gsm) $\pm 5\%$

450

FR Weight (gsm) $\pm 5\%$

UK	550	SIAN	560
----	-----	------	-----

FR Chemical Reference

UK	GreenFR	SIAN	DJ80
----	---------	------	------

Care Instructions

Professional dry clean in situ only

